

# **The Synthesis and Application of Highly Efficient Catalysts for Electrochemical Water Splitting**

**A thesis presented for the award of the degree of Doctor of Philosophy**

**From**

**University of Technology Sydney**

**Faculty of Science**

**By Yufei Zhao, B. Eng.**

**August 2017**

## **DEDICATION**

This thesis is dedicated to my beloved husband, my parents and my sisters

## CERTIFICATION

I, Yufei Zhao, declare that the work in this thesis has not previously been submitted for a degree nor has it been submitted as part of requirements for a degree except as fully acknowledged within the text.

I also declare that the thesis has been written by me. Any help that I have received in my research work and the preparation of the thesis has been acknowledged. In addition, I declare that all information sources and literature used are indicated in the thesis.

This thesis is the result of a research candidature conducted jointly with Beijing Institute of Technology as part of a collaborative Doctoral degree.

Yufei Zhao

Production Note:

Signature removed prior to publication.

---

Sydney,

Australia

08, 2017

## ACKNOWLEDGEMENTS

I would like to express my deep appreciation to my supervisor, Prof. Guoxiu Wang director of Centre for Clean Energy Technology, for his encouragement, understanding, invaluable advice and constant support during my study in University of Technology Sydney (UTS). I appreciate the chance he gave to me for pursuing my PhD in UTS and the innovative ideas for my research.

I am very grateful to Dr Hao. Liu, my co-supervisor, for his constantly rendering helps during my research work. Special thanks for Dr. Yueping (Jane) Yao for her support in the lab, provide me lots of supports. I have my thanks to many people in my research group for their encouragement and brilliant ideas during the period of this research. Dr. Bing Sun, Dr. Dawei Su, Dr. Zhimin Ao, Dr. Shuangqiang Chen, Dr. Xiuqiang Xie, Dr. Anjon Kumar Mondal, Dr. Xiaodan Huang, Mr. Kefei Li, Mr. Jinqiang Zhang, Ms. Jing Xu, Ms. Katja Kretschmer, Mr. Xin Guo and Mr. Weizhai Bao.

I also wish to thank Dr. Ronald Shimmon and Dr. Linda Xiao from School of Mathematical and Physical Sciences in UTS for their friendly support. I would like to give my thanks to Katie McBean and Mark Berkahn from the Microstructural Analysis Unit in UTS for their help on material characterization. I take this chance to mention my cordial thanks to China Scholarship Council (CSC) and Australian Research Council (ARC).

Finally, I would like to thank my husband, Mr. Jinqiang Zhang, and my whole family for their love, understanding, moral support and encouragement during my PhD study. Their love is the mental strength that supported me to

achieve my study abroad.

Yufei Zhao

## TABLE OF CONTENTS

A thesis presented for the award of the degree of Doctor of Philosophy .....	1
DEDICATION .....	I
CERTIFICATION .....	II
ACKNOWLEDGEMENTS .....	III
TABLE OF CONTENTS .....	V
LIST OF FIGURES .....	XII
LIST OF ABBRIEVIATIONS .....	XXIV
LIST OF PUBLICATIONS .....	XXV
ABSTRACT .....	XXIX
INTRODUCTION .....	XXXII
Chapter 1: Literature review .....	1
1.1 Introduction .....	1
1.2 Electrochemistry of water splitting .....	2
1.2.1 The mechanism of electrochemical water splitting .....	2
1.2.2 Electrochemical parameters for the evaluation of HER and OER catalytic activity.....	4
1.2.3 Evaluation criteria of HER and OER catalysts.....	7
1.3 Electrochemical hydrogen evolution reaction .....	7
1.3.1 Mechanism of electrochemical hydrogen evolution reaction.....	8
1.3.2 Catalysts for HER .....	9
1.4 Electrochemical oxygen evolution reaction .....	20
1.4.1 Mechanism of electrochemical oxygen evolution reaction.....	20

1.4.2 Catalysts for OER .....	21
1.4.2.2 Transition metals oxides.....	22
1.5 Bifunctional catalysts for HER and OER.....	31
Chapter 2 experimental method and characterization.....	34
2.1 Overview .....	34
2.2 Material preparation.....	35
2.2.1 Hydrothermal method .....	36
2.2.2 Wet-chemical synthesis.....	36
2.2.3 Chemical redox reaction.....	37
2.2.4 Hard template method .....	37
2.2.5 Electrospinning technique .....	38
2.3 Materials characterization .....	38
2.3.1 X-ray diffraction analysis (XRD) .....	38
2.3.2 Scanning electron microscopy (SEM) .....	40
2.3.3 Transmission electron microscopy (TEM).....	41
2.3.4 Raman spectroscopy .....	42
2.3.5 Brunauer Emmer Teller (BET).....	42
2.3.6 Thermogravimetric analysis (TGA).....	43
2.3.7 X-ray photoelectron spectroscopy (XPS).....	44
2.4 Electrode preparation .....	44
2.4.1 Glassy carbon electrode .....	44
2.4.2 Rotating ring-disk electrode .....	45
2.5 Electrochemical performance characterization .....	46

2.5.1 Linear sweep votammograms (LSV) .....	46
2.5.2 Cyclic voltammetry (CV).....	47
2.5.3 Electrochemical impedance spectroscopy (EIS) .....	47
2.5.4 Stability .....	48
2.5.5 Turnover Frequency (TOF) .....	48
Chapter 3 MoS <sub>2</sub> nanosheets supported on 3D graphene aerogel as a highly efficient catalyst for hydrogen evolution .....	49
3.1 Introduction .....	49
3.2 Experimental.....	51
3.2.1 Synthesis of graphene hydrogel.....	51
3.2.2 Synthesis of graphene hydrogel-MoS <sub>2</sub> .....	51
3.2.3 Synthesis of the comparison materials .....	52
3.2.4 Structural Characterization.....	52
3.2.5 Electrochemical Measurements .....	52
3.3 Results and Discussion.....	53
3.3.1 The characterization of the catalysts .....	53
3.3.2 The electrochemical performance test of the catalysts .....	59
3.4 Conclusion.....	65
Chapter 4 Graphene-Co <sub>3</sub> O <sub>4</sub> nanocomposite as electrocatalyst with high performance for oxygen evolution reaction .....	66
4.1 Introduction .....	66
4.2 Experimental.....	68
4.2.1 The preparation of G-Co <sub>3</sub> O <sub>4</sub> .....	68



4.2.2 The preparation of $\text{Co}_3\text{O}_4$ .....	68
4.2.3 The preparation of Ru/C .....	68
4.2.4 Structural Characterization .....	68
4.2.5 Electrochemical Measurements .....	69
4.3 Results and discussion .....	70
4.3.1 The characterization of the catalysts .....	70
4.3.2 The electrochemical performance test of the catalysts .....	74
4.4 Conclusion .....	79
Chapter 5 Porous graphene wrapped CoO nanoparticles for highly efficient oxygen evolution .....	80
5.1 Introduction .....	80
5.2 Experimental .....	81
5.2.1 Synthesis of porous graphene catalysts (PGE) .....	81
5.2.2 Synthesis of PGE-CoO catalyst .....	82
5.2.3 Synthesis of the comparison catalysts .....	82
5.2.4 Structural Characterization .....	82
5.2.5 Electrochemical Measurements .....	83
5.3 Results and discussion .....	83
5.3.1 The characterization of the catalysts .....	84
5.3.2 The electrochemical performance test of the catalysts .....	88
5.4 Conclusions .....	95
Chapter 6: Ultrathin $\text{CoMn}_2\text{O}_4$ nanosheets with abundant Oxygen Vacancies vertically aligned on Functionalized Carbon Nanofibers as High-Performance Catalyst for Oxygen Evolution .....	97

6.1 Introduction .....	97
6.2 Experimental.....	98
6.2.1 Synthesis of Nitrogen-doped CNFs (NC) .....	98
6.2.2 Synthesis of Cobalt/Nitrogen doped CNFs (CoNC) .....	99
6.2.3 Synthesis of CoMn <sub>2</sub> O <sub>4</sub> nanosheets on CoNC (CoMn <sub>2</sub> O <sub>4</sub> -CoNC) .....	99
6.2.4 Synthesis of MnO <sub>2</sub> nanosheets on NCNFs (MnO <sub>2</sub> -NC) .....	99
6.2.5 Synthesis of Co <sub>3</sub> O <sub>4</sub> nanoparticles on CoNC (Co <sub>3</sub> O <sub>4</sub> -CoNC) .....	100
6.2.6 Characterization .....	100
6.2.7 Electrochemical Measurements .....	101
6.3 Results and discussion.....	102
6.3.1 The characterization of the catalysts .....	102
6.3.2 The electrochemical performance test of the catalysts .....	114
6.4 Conclusion.....	119
Chapter 7: Facile Synthesis and Evaluation of Hierarchical Fe <sub>3</sub> C based Catalyst for High Efficient Oxygen Evolution Reaction .....	121
7.1 Introduction .....	121
7.2 Experimental.....	122
7.2.1 Synthesis of Nitrogen-doped CNFs (NCNFs) .....	122
7.2.2 Synthesis of Fe <sub>3</sub> C@NCNTs-NCNFs .....	123
7.2.3 Characterization .....	123
7.2.4 Electrochemical Measurements .....	124
7.3 Result and discussion .....	125
7.3.1 The characterization of the catalysts .....	126

7.3.2 The electrochemical performance test of the catalysts .....	134
7.4 Conclusion.....	139
Chapter 8 Electrospun Cobalt Embedded in Porous Nitrogen Doped Carbon Nanofibers as an Efficient Catalyst for Water Splitting .....	140
8.1 Introduction .....	140
8.2 Experimental.....	142
8.2.1 Synthesis of Co-PNCNFs.....	142
8.2.2 Synthesis of NCNFs.....	143
8.2.3 Synthesis of the comparison materials.....	143
8.2.4 Characterization .....	143
8.2.5 Electrochemical Measurements .....	144
8.3 Results and discussion.....	145
8.3.1 The characterization of the catalysts.....	145
8.3.2 The electrochemical performance test of the catalysts .....	151
8.4 Conclusions .....	159
Chapter 9 CONCLUSIONS .....	161
9.1 General Conclusion.....	161
9.1.1 MoS <sub>2</sub> nanosheets based material as a highly efficient catalyst for hydrogen evolution .....	161
9.1.2 Cobalt oxide based material as a highly efficient catalyst for oxygen evolution.....	162
9.1.3 Iron carbide based material as a highly efficient catalyst for oxygen evolution.....	163

9.1.4 Carbon based material as highly efficient bi-functional catalyst for water splitting .....	164
9.2 Outlook.....	164
Reference.....	167

## LIST OF FIGURES

<b>Figure 1-1</b> Schematic diagram of an electrolyzer.....	3
<b>Figure 1-2</b> The mechanism of hydrogen evolution on the surface of an electrode in acidic solutions.....	8
<b>Figure 1-3</b> Elements that are used for constructing HER electrocatalysts.....	9
<b>Figure 1-4</b> A volcano plot of experimentally measured exchange current density as a function of the DFT-calculated Gibbs free energy of adsorbed atomic hydrogen. ....	10
<b>Figure 1-5</b> Structure and characterization of atomically thin MoS <sub>2</sub> . (a) Three-dimensional schematic of the atomic structure of MoS <sub>2</sub> . (b) AFM height profile of monolayer MoS <sub>2</sub> ; inset is the corresponding AFM image.....	11
<b>Figure 1-6</b> Typical AFM image of exfoliated nanosheets of WS <sub>2</sub> . Scale bar, 500 nm. (b) High-resolution STEM images of an as-exfoliated WS <sub>2</sub> monolayer showing regions exhibiting the 1T superlattice. Scale bar, 1 nm. ....	13
<b>Figure 1-7</b> Electrochemical measurements of transition metal dichalcogenide films grown on glassy carbon electrodes. (a) Polarization curves of transition metal disulfides, (b) the corresponding Tafel plots. ....	13
<b>Figure 1-8</b> (a) Scheme of the process of WCNCs grown on the tips of VA-CNTs. (b) TEM images of an individual NCs, (c) HER voltammograms of WC-CNTs synthesized at different temperatures in 0.5 M H <sub>2</sub> SO <sub>4</sub> (pH = 0).....	16
<b>Figure 1-9</b> (a) SEM image of Mo-WP/CC, (b) Polarization data for Mo-W-P/CC in 0.50 M H <sub>2</sub> SO <sub>4</sub> electrolyte, along with plots of MoP/CC, WP <sub>2</sub> /CC and Pt/C/CC for comparison.....	18

<b>Figure 1-10</b> (a) Preparation process of MPSA/GO-1000 via cooperative assembly and pyrolysis, (b) Polarization curves of various samples for hydrogen evolution in 0.5 M H <sub>2</sub> SO <sub>4</sub> .....	19
<b>Figure 1-11</b> (a) Synthetic route for the $\gamma$ -CoOOH nanosheets. (b) TEM image and (c) AFM image for the $\gamma$ -CoOOH nanosheets. The inset in (b) shows the HRTEM image for the $\gamma$ -CoOOH nanosheets. (d) XRD pattern for the $\gamma$ -CoOOH nanosheets. The patterns of bulk $\gamma$ -CoOOH and bulk and nanosheet $\alpha$ -Co(OH) <sub>2</sub> are also displayed for comparison.....	22
<b>Figure 1-12</b> (a) Schematic of the spatially confined hybrids and crosssectional TEM image of a sheet of nNiFe LDH/NGF electrocatalyst. (b, c) polarization curves and Tafel slope of nNiFe LDH/NGF and other samples for comparison. (d) Figures of merit with respect to both kinetics (Tafel slope) and activity (the overpotential required to achieve 10 mA cm <sup>-2</sup> ), with references all measured in 0.1 M KOH electrolyte. ....	25
<b>Figure 1-13</b> polarization curves of Mn-based catalysts towards OER. ....	26
<b>Figure 1-14</b> (a) A unit cell in perovskite showing relative positions of different ions, (b) The relation between the OER catalytic activity, defined by the overpotentials at 50 mA cm <sup>-2</sup> <sub>ox</sub> of the OER current, and the occupancy of the e <sub>g</sub> -symmetry electron of the transition metal (B in ABO <sub>3</sub> ). ....	27
<b>Figure 1-15</b> (a) Molecular cobalt complexes, (b) CV of 5 recorded in phosphate buffer solution (0.1 mM, pH 9.2) with a scan rate of 50 mV s <sup>-1</sup> (red), and a blank scan without 5 under the same conditions (black). ....	28
<b>Figure 1-16</b> Structures of nicke(II) complexes used as precatalysts. ....	29
<b>Figure 1-17</b> (a-c) SEM and TEM images of the N/C, (d) Oxygen evolution activities of the N/C, N/C-NiO <sub>x</sub> , IrO <sub>2</sub> /C (20 wt%) and Pt/C (20 wt%) electrodes with KOH electrolyte (pH 13). ....	30

<b>Figure 1-18</b> (a) Polarization curve showing the bifunctionality of CP@Ni-P toward both HER and OER. (b) Polarization curve in a two-electrode configuration. (c) Chronopotentiometric curve of water electrolysis at several different current densities. (d) Energy efficiency of the CP@Ni-P electrolyzer as a function of current density. (e) Long-term durability tests made at 10 and 20 mA cm <sup>-2</sup> . (f) A digital photograph showing the evolution of H <sub>2</sub> and O <sub>2</sub> gas from the electrodes at 20 mA cm <sup>-2</sup> .....	32
<b>Figure 2-1</b> Schematic illustration for materials preparations, characterizations and applications. ....	34
<b>Figure 2-2</b> Autoclaves for hydrothermal synthesis.....	36
<b>Figure 2-3</b> The electrospinning instrument for the experiment.....	38
<b>Figure 2-4</b> The Bruker D8 Discover XRD instrument.....	39
<b>Figure 2-5</b> The field emission scanning electron microscopy in a mode of Supra 55 VP produced by Zeiss and equipped with EDS detector. ....	40
<b>Figure 2-6</b> Transmission electron microscopy (TEM, Model JEM-2011, JEOL). ....	41
<b>Figure 2-7</b> The Renishaw inVia Raman microscope equipped with a Leica DMLB microscope (Wetzlar, Germany) and a 17 mW at 633 nm Renishaw helium neon laser. ....	42
<b>Figure 2-8</b> The 3 Flex surface characterization analyser instrument produced by Micromeritics. ....	43
<b>Figure 2-9</b> The three-electrode system.....	44
<b>Figure 2-10</b> The Pine rotating ring-disk electrode (RRDE) instrument. ....	45
<b>Figure 3-1</b> Schematic illustration for the synthesis procedure of GA-MoS <sub>2</sub> composite.....	53
<b>Figure 3-2</b> Electron microscope characterization of GA and GA-MoS <sub>2</sub> : a, b) low and high magnification SEM images of GA, c, d) low and high magnification SEM images of GA-MoS <sub>2</sub> , e, f) low and high magnification TEM images of GA-MoS <sub>2</sub> .....	54

<b>Figure 3-3</b> SEM image and EDS elemental mappings of GA-MoS <sub>2</sub> , (a) SEM image of GA-MoS <sub>2</sub> , (b) EDS profile, (c) element of O, (d) element of S, (e) element of Mo, (f) element of C.....	55
<b>Figure 3-4</b> (a) XRD patterns and (b) Raman spectra of GA and GA-MoS <sub>2</sub> .....	56
<b>Figure 3-5</b> (a) XPS survey spectrum of GA-MoS <sub>2</sub> composite, high-resolution XPS spectra of GA-MoS <sub>2</sub> c) Mo 3d, d) S 2p. (d) thermogravimetric analysis in air of GA-MoS <sub>2</sub> and MoS <sub>2</sub> in air, used for calculating the content of MoS <sub>2</sub> in GA-MoS <sub>2</sub> composite.....	57
<b>Figure 3-6</b> SEM images of (a) G-MoS <sub>2</sub> and (b) pure MoS <sub>2</sub> .....	58
<b>Figure 3-7</b> Nitrogen adsorption/desorption isotherm of (a) GA, (b) GA-MoS <sub>2</sub> , (c) G-MoS <sub>2</sub> , (d) pure MoS <sub>2</sub> . .....	59
<b>Figure 3-8</b> Electrochemical performance of the HER catalysts in 0.5 M H <sub>2</sub> SO <sub>4</sub> : a) polarization curves for GA-MoS <sub>2</sub> , G-MoS <sub>2</sub> , MoS <sub>2</sub> and GA loaded onto GC electrodes; b) Tafel curves of GA-MoS <sub>2</sub> , G-MoS <sub>2</sub> and MoS <sub>2</sub> . .....	60
<b>Figure 3-9</b> Electrochemical capacitance measurements: Cyclic voltammograms are performed in 0.5 M H <sub>2</sub> SO <sub>4</sub> solution in a potential window without faradaic processes and the scan rate from 10 to 100 mV s <sup>-1</sup> , (a) GA-MoS <sub>2</sub> , (b) G-MoS <sub>2</sub> , (c) MoS <sub>2</sub> . (d) scan rate dependence of the average capacitive current densities at open circuit potential for GA-MoS <sub>2</sub> , G-MoS <sub>2</sub> and MoS <sub>2</sub> . .....	61
<b>Figure 3-10</b> (a) Nyquist and (b) Bode plots for GA-MoS <sub>2</sub> hybrid modified GC electrode recorded at various HER overpotentials in 0.5 M H <sub>2</sub> SO <sub>4</sub> ; (c) Nyquist and (d) Bode plots for G-MoS <sub>2</sub> hybrid. (e) Equivalent electrical circuit used to model the HER process on GA-MoS <sub>2</sub> and G-MoS <sub>2</sub> modified GC electrodes at various overpotentials, (f) the square symbols are experimental data and the red solid line are modelled by (e).....	63
<b>Figure 3-11</b> (a) stability test of GA-MoS <sub>2</sub> through potential cycling, polarization curves before and after 2000 potential cycles, (b) polarization curves of GA-MoS <sub>2</sub> at different scan rates, and the inset of d) shows the	



corresponding data of the current density (at -0.2 V vs SHE) vs scan rate.....	64
<b>Figure 4-1</b> A schematic illustration for preparing G-Co <sub>3</sub> O <sub>4</sub> nanocomposite with a sandwich-architecture.....	70
<b>Figure 4-2</b> Microscope observation of the G-Co <sub>3</sub> O <sub>4</sub> composite. (a) Low and high magnification SEM images of G-Co <sub>3</sub> O <sub>4</sub> . (b) Low magnification TEM image of G-Co <sub>3</sub> O <sub>4</sub> . (c) High resolution TEM (HRTEM) image of G-Co <sub>3</sub> O <sub>4</sub> , showing a sandwich-like microstructure. (d) HRTEM image of Co <sub>3</sub> O <sub>4</sub> nanocrystals and SAED pattern of G- Co <sub>3</sub> O <sub>4</sub> .....	71
<b>Figure 4-3</b> The SEM image of pristine Co <sub>3</sub> O <sub>4</sub> .....	72
<b>Figure 4-4</b> The characterization of the G-Co <sub>3</sub> O <sub>4</sub> composite: (a) XRD patterns of Co <sub>3</sub> O <sub>4</sub> and G-Co <sub>3</sub> O <sub>4</sub> composite. (b) Raman spectra of Co <sub>3</sub> O <sub>4</sub> and G-Co <sub>3</sub> O <sub>4</sub> composite catalyst.....	73
<b>Figure 4-5</b> Electrochemical performance: (a) Polarization curves of G-Co <sub>3</sub> O <sub>4</sub> and Ru/C catalysts on GC electrodes in 0.1 and 1 M KOH. (b) The Tafel curves of G-Co <sub>3</sub> O <sub>4</sub> in 0.1 and 1 M KOH. (c, d) Chronoamperometric responses (percentage of current retained versus operation time) of G-Co <sub>3</sub> O <sub>4</sub> and Ru/C catalysts in 1 M and 0.1 M KOH electrolytes. ....	74
<b>Figure 4-6</b> Electrochemical performance of G-Co <sub>3</sub> O <sub>4</sub> composite OER catalyst: (a) LSV and Tafel slope of G-Co <sub>3</sub> O <sub>4</sub> in neutral solution, (b) OER stability test of G-Co <sub>3</sub> O <sub>4</sub> , the initial and 1000th polarization curves in neutral solution.....	76
<b>Figure 4-7</b> Electrochemical performance: Polarization curves of G-Co <sub>3</sub> O <sub>4</sub> , G+Co <sub>3</sub> O <sub>4</sub> , the pristine Co <sub>3</sub> O <sub>4</sub> and graphene in (a) 1 M and (b) 0.1 M KOH solutions.....	77
<b>Figure 4-8</b> Nyquist plots of the G-Co <sub>3</sub> O <sub>4</sub> , the G+Co <sub>3</sub> O <sub>4</sub> and the pristine Co <sub>3</sub> O <sub>4</sub> modified electrodes in 1M KOH solution.....	78
<b>Figure 4-9</b> (a, c) Electrochemical capacitance measurements: typical Cyclic voltammograms (CV) of G-Co <sub>3</sub> O <sub>4</sub> and G+Co <sub>3</sub> O <sub>4</sub> measured in 1 M	

KOH solution in a potential window without faradaic processes (scan rate: 10, 30, 50, 70, 90 mV/s); (b, d) Average capacitive current obtained from center of potential window (-0.12 V vs Ag/AgCl) as a function of scan rate for G-Co <sub>3</sub> O <sub>4</sub> and G+Co <sub>3</sub> O <sub>4</sub> electrodes. ....	78
<b>Figure 5-1</b> SEM image of silica nanorod templates for the synthesis of PGE. ....	84
<b>Figure 5-2</b> Schematic illustration for the synthesis procedure of PGE-CoO materials. ....	84
<b>Figure 5-3</b> (a) Nitrogen adsorption/desorption isotherm of PGE, (b) SEM image of PGE. ....	85
<b>Figure 5-4</b> The characterization of PGE-CoO hybrid: (a, b) low and high magnification SEM images of PGE-CoO, (c, d) TEM images of PGE-CoO. ....	86
<b>Figure 5-5</b> (a, b) SEM images of pure CoO and GE-CoO, (c, d) Nitrogen adsorption/desorption isotherm of PGE-CoO and GE-CoO. ....	87
<b>Figure 5-6</b> (a) XRD patterns of PGE-CoO and PGE, high-resolution spectra XPS (b) Co 2p, (c) O 1s, (d) thermogravimetric analysis in air of PGE-CoO. ....	88
<b>Figure 5-7</b> Electrochemical performance of the OER catalysts: (a) polarization curves for PGE-CoO, GE-CoO, CoO and PGE on GC electrodes in 0.1 M KOH. (b) Tafel curves of PGE-CoO, GE-CoO and CoO in 0.1 M KOH. (c) Nyquist plots of the PGE-CoO, GE-CoO and CoO modified electrodes in 0.1 M KOH solution. (d, e) electrochemical capacitance measurements: cyclic voltammograms (CV) were performed in 0.1 M KOH solution in a potential window without faradaic processes. (f) scan rate dependence of the average capacitive currents at -0.08 V vs Ag/AgCl for PGE-CoO and GE-CoO. ....	90
<b>Figure 5-8</b> (a) Nyquist and (b) Bode plots for the PGE-CoO hybrid modified GC electrode recorded at various OER overpotentials in 0.1 M KOH, (c) the square symbols are experimental data and the red solid line are	

modelled by the Equivalent electrical circuit shown in the inset, (d) the low-frequency charge transfer resistance ( $R_{ct}$ ) and constant phase element ( $C_{dl}$ ) as a function of the OER overpotentials for PGE-CoO-modified GC electrode in 0.1 M KOH. ....	91
<b>Figure 5-9</b> (a) The stability of PGE-CoO and GE-CoO modified electrodes before and after LSV testing for 1000 cycles, (b, c) SEM images of PGE-CoO and GE-CoO after stability test. ....	93
<b>Figure 5-10</b> (a) Polarization curves for PGE-CoO in various KOH concentrations. (b) current densities at 0.7 V vs. Ag/AgCl for PGE-CoO in solutions with various KOH concentrations. ....	95
<b>Figure 6-1</b> schematic illustration for the fabrication process of $\text{CoMn}_2\text{O}_4\text{-CoNC}$ . ....	102
<b>Figure 6-2</b> (a, b) SEM and TEM images of CoNC; (c) XRD pattern of CoNC...	103
<b>Figure 6-3</b> (a, b) the low and high magnification SEM images of $\text{CoMn}_2\text{O}_4\text{-CoNC}$ . ....	103
<b>Figure 6-4</b> (a-c) low and high magnification TEM images of $\text{CoMn}_2\text{O}_4\text{-CoNC}$ ; STEM element mapping of $\text{CoMn}_2\text{O}_4\text{-CoNC}$ : (d) high angle annular dark field (HAADF) image showing the area of mapping, (e-g) element mapping in STEM mode for Mn, Co and O elements.....	104
<b>Figure 6-5</b> (a, b) XRD and Raman spectra of $\text{CoMn}_2\text{O}_4\text{-CoNC}$ . ....	105
<b>Figure 6-6</b> (a) XPS survey spectra of $\text{CoMn}_2\text{O}_4\text{-CoNC}$ , high resolution XPS spectra of $\text{CoMn}_2\text{O}_4\text{-CoNC}$ , (b) N 1s, (c) Mn 2p, (d) Co 2p, (e) O 1s. ....	106
<b>Figure 6-7</b> (a) Nitrogen adsorption/desorption isotherm and (b) pore size distribution of $\text{CoMn}_2\text{O}_4\text{-CoNC}$ .....	107
<b>Figure 6-8</b> (a) SEM image of pure NCNFs, (b) SEM image, (c) XRD spectrum, (d) XPS survey spectrum of $\text{MnO}_2\text{-NC}$ . ....	108

<b>Figure 6-9</b> Typical SEM images of the products after reaction for (a, e) 20 min, (b, f) 1 h, (c, g) 4 h and (d, h) 8 h. (i) Schematic illustration of the formation procedure of CoMn <sub>2</sub> O <sub>4</sub> -CoNC composite. ....	109
<b>Figure 6-10</b> (a, b) SEM images of CoMn <sub>2</sub> O <sub>4</sub> -CoNC obtained after 15 h reaction. ....	110
<b>Figure 6-11</b> (a) XRD and (b) Raman spectra of CoMn <sub>2</sub> O <sub>4</sub> -CoNC obtained at different time.....	111
<b>Figure 6-12</b> (a) XPS survey spectra, high resolution XPS spectra of (b) Co 2p, (c) Mn 2p, (d) O 1s of CoMn <sub>2</sub> O <sub>4</sub> -CoNC obtained at different time.....	112
<b>Figure 6-13</b> Low and high SEM images of NiMn <sub>2</sub> O <sub>4</sub> -NiNC. ....	113
<b>Figure 6-14</b> (a) polarization curves and (b) corresponding Tafel plots of CoMn <sub>2</sub> O <sub>4</sub> -CoNC, MnO <sub>2</sub> -NC, Co <sub>3</sub> O <sub>4</sub> -CoNC, NC and RuO <sub>2</sub> .....	114
<b>Figure 6-15</b> Cyclic voltammograms (CV) of (a) CoMn <sub>2</sub> O <sub>4</sub> -CoNC, (b) Co <sub>3</sub> O <sub>4</sub> -CoNC and (c) MnO <sub>2</sub> -NC, in 1 M KOH solution in a potential window without faradaic processes. (c) Scan rate dependence of the average capacitive current densities at open circuit potential for CoMn <sub>2</sub> O <sub>4</sub> -CoNC, Co <sub>3</sub> O <sub>4</sub> -CoNC and MnO <sub>2</sub> -NC. ....	115
<b>Figure 6-16</b> Nyquist plots of the as-prepared samples modified electrodes recorded at a constant overpotential of 250 mV.....	116
<b>Figure 6-17</b> Stability test of CoMn <sub>2</sub> O <sub>4</sub> -CoNC through potential cycling, the inset shows the time dependence of catalytic current density during electrolysis at a static potential. ....	117
<b>Figure 6-18</b> (a) Evidence of O <sub>2</sub> generated from CoMn <sub>2</sub> O <sub>4</sub> -CoNC catalyst using RRDE measurements (1600 rpm) (disk potential: 1.48 V, ring potential: 0.45 V vs. RHE), with inset showing the continuous OER → ORR process initiated on the RRDE. (b) Disk and ring current of CoMn <sub>2</sub> O <sub>4</sub> -CoNC catalyst on an RRDE (1600 rpm) with a ring potential of 1.5 V (vs. RHE).....	118

<b>Figure 7-1</b> (a) Schematic illustration for the fabrication process of Fe <sub>3</sub> C@NCNTs-NCNFs. (b) low and (c, d) high magnification SEM images of Fe <sub>3</sub> C@NCNTs-NCNFs.....	126
<b>Figure 7-2</b> (a) TEM image of a single fibrous Fe <sub>3</sub> C@NCNTs-NCNF. (b) HRTEM image of Fe <sub>3</sub> C@NCNTs aligned on NCNF. (c) high resolution TEM image of a single Fe <sub>3</sub> C@NCNT. (d) a Fe <sub>3</sub> C nanoparticle wrapped by multilayered graphitic carbon, the enlarged area as denoted in the white box, displaying an interplanar spacing of 0.239 nm. (e-i) STEM elemental mapping of Fe <sub>3</sub> C@NCNTs-NCNFs. (j-l) two different phases of Fe <sub>3</sub> C@NCNTs-NCNFs, (k) C, (l) Fe <sub>3</sub> C. ....	127
<b>Figure 7-3</b> (a,b) SEM and (c,d) TEM images of NCNFs.....	129
<b>Figure 7-4</b> (a) SEM and (b-d) TEM images of Fe <sub>3</sub> C-NCNFs. ....	129
<b>Figure 7-5</b> (a, b) XRD pattern of Fe <sub>3</sub> C@NCNTs-NCNFs and Fe <sub>3</sub> C-NCNFs.....	130
<b>Figure 7-6</b> Raman spectra of Fe <sub>3</sub> C@NCNTs-NCNFs, Fe <sub>3</sub> C-NCNFs and pure NCNFs. ....	131
<b>Figure 7-7</b> (a) XPS survey spectrum of Fe <sub>3</sub> C@NCNTs-NCNFs. high resolution XPS spectra of (b) C 1s, (c) Fe 2p and (d) N 1s of Fe <sub>3</sub> C@NCNTs-NCNFs composite. ....	132
<b>Figure 7-8</b> (a) Nitrogen sorption isotherm Fe <sub>3</sub> C@NCNTs-NCNFs. (b) Thermogravimetric analysis of Fe <sub>3</sub> C@NCNTs-NCNFs in air. ....	133
<b>Figure 7-9</b> (a) polarization curves and (b) corresponding Tafel plots of Fe <sub>3</sub> C@NCNTs-NCNFs, Fe <sub>3</sub> C-NCNFs, NCNFs and RuO <sub>2</sub> . ....	134
<b>Figure 7-10</b> Cyclic voltammograms (CV) of (a) Fe <sub>3</sub> C@NCNTs-NCNFs, (b) Fe <sub>3</sub> C-NCNFs, (c) NCNFs, both in 1 M KOH solution in a potential window without faradaic processes. (d) Scan rate dependence of the average capacitive current densities at open circuit potential for Fe <sub>3</sub> C@NCNTs-NCNFs, Fe <sub>3</sub> C-NCNFs and NCNFs.....	135
<b>Figure 7-11</b> EIS spectra of Fe <sub>3</sub> C@NCNTs-NCNFs, Fe <sub>3</sub> C-NCNFs and NCNFs modified electrodes with an overpotential of 250 mV.....	136

<b>Figure 7-12</b> Stability test of Fe <sub>3</sub> C@NCNTs-NCNFs (a) through potential cycling. (b) time dependence of catalytic current density during electrolysis at a static overpotential.....	136
<b>Figure 7-13</b> (a) Disk and ring current of Fe <sub>3</sub> C@NCNTs-NCNFs catalyst on an RRDE (1600 rpm) with a ring potential of 1.50 V (vs. RHE). (b) Evidence of O <sub>2</sub> generated from Fe <sub>3</sub> C@NCNTs-NCNFs catalyst using RRDE measurements (1600 rpm) (disk potential: 1.48 V, ring potential: 0.45 V vs. RHE), with inset showing the continuous OER → ORR process initiated on the RRDE. ....	137
<b>Figure 8-1</b> Schematic illustration for the preparation of Co-PNCNFs nanofibers by electrospinning. ....	146
<b>Figure 8-2</b> SEM image of Co-NCNFs (before acid treatment), showing the cobalt nanoparticles on the surface of CNFs. ....	146
<b>Figure 8-3</b> Electron microscopy characterization of Co-PNCNFs. (a) low magnification and (b) high magnification SEM images of Co-PNCNFs. (c) EDS analysis of Co-PNCNFs, showing homogenous distribution of C, N, Co elements in fibrous structure. (d) TEM image of a single fibrous Co-PNCNF. (e) Enlarged TEM image of a single Co-PNCNF, demonstrating the structure of dispersed nanoparticles embedded in porous carbon fiber. (f) HRTEM image of a Co nanoparticle wrapped in carbon. The inset is the enlarged area as denoted in the white box, displaying an interplanar spacing of 0.205 nm. ....	147
<b>Figure 8-4</b> (a, b) Low and high magnification SEM images of NCNFs, (c, d) Low and high magnification TEM images of NCNFs. ....	149
<b>Figure 8-5</b> (a) XRD patterns of NCNFs and Co-PNCNFs. (b) Raman spectra of NCNFs and Co-PNCNFs. (c) XPS spectrum of Co-PNCNFs composite. High resolution XPS spectra of (d) Co 2p and (e) N 1s. (f) Nitrogen sorption isotherm of Co-PNCNFs, inset shows the pore size distribution of Co-PNCNFs. ....	150

- Figure 8-6** Electrochemical performance of the catalysts towards OER in 1 M KOH solution: (a) Polarization curves for Co-PNCNFs, NCNFs, RuO<sub>2</sub>, Pt/C and pure GC. (b) The corresponding Tafel plots of catalysts. ... 152
- Figure 8-7** Cyclic voltammograms (CV) of (a) Co-PNCNFs, and (b) NCNFs, both in 1 M KOH solution in a potential window without faradaic processes. (c) Scan rate dependence of the average capacitive current densities at open circuit potential for Co-PNCNFs and NCNFs. (d) Nyquist plots of Co-PNCNFs and NCNFs modified electrodes. .... 153
- Figure 8-8** (a) Stability test of Co-PNCNFs through potential cycling, displaying polarization curves of initial one, after 1000 and 5000 potential cycles. Inset shows the chronoamperometric stability test over 12 h. (b) SEM image of Co-PNCNFs after stability test (60 h), displaying the carbon matrix and porous structure were maintained. .... 154
- Figure 8-9** (a) The ring current of Co-PNCNFs on a RRDE (1600 rpm) in a N<sub>2</sub>-saturated 1 M KOH solution (ring potential: 0.45 V *vs.* RHE). (b) Disk and ring current of Co-PNCNFs on a RRDE (1600 rpm) with a disk potential of 1.55 V (*vs.* RHE) and ring potential of 1.50 V (*vs.* RHE) in 1 M KOH solution. .... 155
- Figure 8-10** Catalytic activities of (a) Co-PNCNFs, Ni-PNCNFs, Fe-PNCNFs and pure NCNFs, and (b) Co-PNCNFs, Co-PCNFs and NCNFs. All these catalytic activity of CNFs based materials towards OER were tested in 1 M KOH solution, showing the electrocatalytic improvements promoted by metal or N functionalization. .... 156
- Figure 8-11** Electrochemical performance of the catalysts towards HER in 1 M KOH solution: (a) polarization curves for Co-PNCNFs, NCNFs, Pt/C and bare GC. (b) The corresponding Tafel plots. .... 158
- Figure 8-12** Electrochemical performance test of Co-PNCNFs deposited on nickel foam towards (a) OER and (b) HER in 1 M KOH solution. (c) Optical photograph of Co-PNCNFs based electrolyzer. (d) LSV of water

electrolysis using Co-PNCNFs as both OER and HER catalysts. The inset shows the stability test at the potential of 1.66 V over 10 h.... 159



## LIST OF ABBREVIATIONS

---

Abbreviation	Full name
a.u.	Arbitrary unit
nm	Nanometer
cm	Centimeter
LSV	Linear sweep voltammetry
CV	Cyclic voltammetry
EIS	Electrochemical impedance spectroscopy
RRDE	Rotating ring-disk electrode
GC	Glassy carbon electrode
RHE	Reversible hydrogen electrode
GC	Glassy carbon electrode
Eq.	Equation
JCPDS	Joint committee on powder diffraction standards
SAED	Selected area electron diffraction
SEM	Scanning electron microscopy
TEM	Transmission electron microscopy
XPS	X-ray photoelectron spectroscopy
BET	Brunauer Emmett Teller
TGA	Thermogravimetric analysis
XRD	X-ray diffraction
FT-IR	Fourier transform infrared spectroscopy
DMF	Dimethylformamide
DMDMS	Dimethoxydimethylsilane
TEOS	Tetraethyl orthosilicate
CTAB	Hexadecyl trimethyl ammonium bromide
OCP	Open circuit potential
HER	Hydrogen evolution reaction
OER	Oxygen evolution reaction

---

## LIST OF PUBLICATIONS

- [1] **Zhao, Y.**; Zhang, Y.; Yang, Z.; Yan, Y.; Sun, K. Synthesis of MoS<sub>2</sub> and MoO<sub>2</sub> for their applications in H<sub>2</sub> generation and lithium ion batteries: a review. *Science and Technology of Advanced Materials* 2013, 14, 043501.
- [2] **Zhao, Y.**; Chen, S.; Sun, B.; Su, D.; Huang, X.; Liu, H.; Yan, Y.; Sun, K.; Wang, G. Graphene-Co<sub>3</sub>O<sub>4</sub> nanocomposite as electrocatalyst with high performance for oxygen evolution reaction. *Scientific reports* 2015, 5, 7629.
- [3] **Zhao, Y.**; Yang, Z.-Y.; Zhang, Y.-X.; Jing, L.; Guo, X.; Ke, Z.; Hu, P.; Wang, G.; Yan, Y.-M.; Sun, K.-N. Cu<sub>2</sub>O decorated with cocatalyst MoS<sub>2</sub> for solar hydrogen production with enhanced efficiency under visible light. *The Journal of Physical Chemistry C* 2014, 118, 14238-14245.
- [4] **Zhao, Y.**; Xie, X.; Zhang, J.; Liu, H.; Ahn, H. J.; Sun, K.; Wang, G. MoS<sub>2</sub> Nanosheets Supported on 3D Graphene Aerogel as a Highly Efficient Catalyst for Hydrogen Evolution. *Chemistry—A European Journal* 2015, 21, 15908-15913.
- [5] **Zhao, Y.**; Sun, B.; Huang, X.; Liu, H.; Su, D.; Sun, K.; Wang, G. Porous graphene wrapped CoO nanoparticles for highly efficient oxygen evolution. *Journal of Materials Chemistry A* 2015, 3, 5402-5408.
- [6] **Zhao, Y.**; Zhang, J.; Li, K.; Ao, Z.; Wang, C.; Liu, H.; Sun, K.; Wang, G. Electrospun cobalt embedded porous nitrogen doped carbon nanofibers as an efficient catalyst for water splitting. *Journal of Materials Chemistry A* 2016, 4, 12818-12824.
- [7] Jing, L.; Yang, Z.-Y.; **Zhao, Y.**; Zhang, Y.-X.; Guo, X.; Yan, Y.-M.; Sun, K.-N. Ternary polyaniline–graphene–TiO<sub>2</sub> hybrid with enhanced activity for visible-

- light photo-electrocatalytic water oxidation. *Journal of Materials Chemistry A* 2014, 2, 1068-1075.
- [8] Yang, Z.-Y.; **Zhao, Y.**; Xiao, Q.-Q.; Zhang, Y.-X.; Jing, L.; Yan, Y.-M.; Sun, K.-N. Controllable growth of CNTs on graphene as high-performance electrode material for supercapacitors. *ACS applied materials & interfaces* 2014, 6, 8497-8504.
- [9] Wang, X.; Yang, Z.; Zhang, Y.; Jing, L.; **Zhao, Y.**; Yan, Y.; Sun, K. MnO<sub>2</sub> Supported Pt Nanoparticels with High Electrocatalytic Activity for Oxygen Reduction Reaction. *Fuel Cells* 2014, 14.
- [10] Zhang, W.; Zhang, Y.; Tian, Y.; Yang, Z.; Xiao, Q.; Guo, X.; Jing, L.; **Zhao, Y.**; Yan, Y.; Feng, J. Insight into the capacitive properties of reduced graphene oxide. *ACS applied materials & interfaces* 2014, 6, 2248-2254.
- [11] Yang, Z.; Zhang, L.; Zhang, Y.; **Zhao, Y.**; Jing, L.; Yan, Y.; Sun, K. Rational design of CuO@ Cu nanostructure with tuneable morphology and electrochemical properties. *RSC Advances* 2014, 4, 8121-8124.
- [12] Sun, B.; Huang, X.; Chen, S.; **Zhao, Y.**; Zhang, J.; Munroe, P.; Wang, G. Hierarchical macroporous/mesoporous NiCo<sub>2</sub>O<sub>4</sub> nanosheets as cathode catalysts for rechargeable Li-O<sub>2</sub> batteries. *Journal of Materials Chemistry A* 2014, 2, 12053-12059.
- [13] Huang, X.; **Zhao, Y.**; Ao, Z.; Wang, G. Micelle-template synthesis of nitrogen-doped mesoporous graphene as an efficient metal-free electrocatalyst for hydrogen production. *Scientific reports* 2014, 4, 7557.

- [14] Chen, S.; **Zhao, Y.**; Sun, B.; Ao, Z.; Xie, X.; Wei, Y.; Wang, G. Microwave-assisted synthesis of mesoporous  $\text{Co}_3\text{O}_4$  nanoflakes for applications in lithium ion batteries and oxygen evolution reactions. *ACS applied materials & interfaces* 2015, 7, 3306-3313.
- [15] Xu, J.; Su, D.; Bao, W.; **Zhao, Y.**; Xie, X.; Wang, G. Rose flower-like  $\text{NiCo}_2\text{O}_4$  with hierarchically porous structures for highly reversible lithium storage. *Journal of Alloys and Compounds* 2016, 684, 691-698.
- [16] Kretschmer, K.; Sun, B.; Su, D.; **Zhao, Y.**; Wang, G. Scalable Preparation of  $\text{LiFePO}_4/\text{C}$  Nanocomposites with  $\text{sp}^2$ -Coordinated Carbon Coating as High-Performance Cathode Materials for Lithium-Ion Batteries. *ChemElectroChem* 2015, 2, 2096-2103.
- [17] Zhang, J.; Sun, B.; Xie, X.; **Zhao, Y.**; Wang, G. A Bifunctional Organic Redox Catalyst for Rechargeable Lithium-Oxygen Batteries with Enhanced Performances. *Advanced Science* 2015, 3, 1500285.
- [18] Zhang, J.; Sun, B.; McDonagh, A. M.; **Zhao, Y.**; Kretschmer, K.; Guo, X.; Wang, G. A multi-functional gel co-polymer bridging liquid electrolyte and solid cathode nanoparticles: An efficient route to  $\text{Li-O}_2$  batteries with improved performance. *Energy Storage Materials* 2017, 7, 1-7.
- [19] Guo, X.; Xie, X.; Choi, S.; **Zhao, Y.**; Liu, H.; Wang, C.; Chang, S.; Wang, G.  $\text{Sb}_2\text{O}_3/\text{MXene}$  ( $\text{Ti}_3\text{C}_2\text{T}_x$ ) hybrid anode materials with enhanced performance for sodium-ion batteries. *Journal of Materials Chemistry A* 2017, 5, 12445-12452.

- [20] Zhang, J.; Sun, B.; **Zhao, Y.**; Kretschmer, K.; Wang, G. Modified Tetrathiafulvalene as an Organic Conductor for Improving Performances of Li-O<sub>2</sub> Batteries. *Angewandte Chemie International Edition* 2017, 56, 8505-8509 .

## ABSTRACT

Hydrogen ( $H_2$ ) is an abundant and renewable clean fuel that is regarded as a promising energy carrier to replace fossil fuels in the future. Electrocatalytic water splitting to produce  $H_2$  seems to be one of the cleanest and most sustainable methods for large-scale  $H_2$  production. The catalysts are of extreme significance for the electrochemical performances of water splitting.

The composite of layered  $MoS_2$  nanosheets supported on a 3D graphene aerogel network (GA- $MoS_2$ ) has been synthesized by two-step hydrothermal method. The flexible graphene sheets partially overlap in 3D space to form an interconnected porous microstructure, which greatly prevents serious restacking of graphene, and further provides large surface area for growing  $MoS_2$  nanosheets. GA- $MoS_2$  maintains an excellent porous structure and assembles with  $MoS_2$  nanosheets around the edge of the pores, providing relatively large amounts of exposed edge sites for hydrogen evolution. The 3D structure of the catalyst can also supply efficient conducting network for rapid electronic transport during the electrocatalytic process, offsetting the poor intrinsic conductivity of  $MoS_2$ , facilitating fast electron transfer. Therefore, GA- $MoS_2$  exhibits high catalytic performance and strong stability for electrocatalytic HER application.

Graphene- $Co_3O_4$  composite with a unique sandwich-architecture is successfully synthesized and applies as an efficient electrocatalyst towards OER. The graphene nanosheets act as a binder to link neighboring  $Co_3O_4$  particles together and  $Co_3O_4$  nanocrystals are homogeneously attached on both sides of graphene nanosheets. The existence of graphene highly increases the conductivity of the composite. The obtained composite shows enhanced

catalytic activities in both alkaline and neutral electrolytes. The current density of  $10 \text{ mA cm}^{-2}$  has been achieved at the overpotential of 313 mV in 1 M KOH and 498 mV in phosphate buffer solution, respectively. Furthermore, there is no obvious current density decay after the stability test.

An active catalyst composed of porous graphene and cobalt oxide (PGE–CoO) has been synthesized, demonstrating high porosity, large specific surface area and fast charge transport kinetics. The catalyst also exhibits excellent electrochemical performance towards OER with a low onset potential (504 mV vs. Ag/AgCl) and high catalytic current density (overpotential of 348 mV for  $10 \text{ mA cm}^{-2}$ ). The enhanced catalytic activity could be ascribed to porous structure, high electroactive surface area and strong chemical coupling between graphene and CoO nanoparticles. Moreover, CoO nanoparticles are wrapped by the porous graphene, inhibiting the corrosion phenomenon, thus this OER catalyst also shows good stability in the alkaline solution. The high performance and strong durability suggest that the porous structured composite is favorable and promising for water splitting.

We develop ultrathin  $\text{CoMn}_2\text{O}_4$  nanosheets with abundant oxygen vacancies vertically aligned on cobalt and nitrogen co-functionalized carbon nanofibers ( $\text{CoMn}_2\text{O}_4\text{-CoNC}$ ) as an efficient OER catalyst by a facial spontaneous redox reaction. The inner CoNC serves as sacrificed template and high conductive substrate to provide fast electronic transportation, and the aligned ultrathin nanosheets rich in oxygen vacancies act as active sites. Benefiting from the collaborative advantages of high effective surface areas, fast charge transfer kinetics and strong synergistic coupled effect,  $\text{CoMn}_2\text{O}_4\text{-CoNC}$  composite exhibits excellent catalytic activity and good durability for

water oxidation, reaching  $10 \text{ mA cm}^{-2}$  at an overpotential of 307 mV.

$\text{Fe}_3\text{C}$  nanoparticles encapsulated at the tip of nitrogen-enriched carbon nanotubes (NCNTs) is investigated as catalyst for OER, which are aligned on one dimensional (1D) nitrogen doped carbon nanofibers ( $\text{Fe}_3\text{C}@\text{NCNTs-NCNFs}$ ) by a scalable electrospinning technique, as a high performance OER catalyst. The unique 3D hierarchical architecture of  $\text{Fe}_3\text{C}@\text{NCNTs-NCNFs}$  leads to highly exposed active sites, enhanced electron transfer properties and strong synergistic coupled effects.  $\text{Fe}_3\text{C}@\text{NCNTs-NCNFs}$  exhibits outstanding catalytic performance with a high current density ( $10 \text{ mA cm}^{-2}$  at an overpotential of 284 mV), a low Tafel slope ( $56 \text{ mV dec}^{-1}$ ), a low charge transfer resistance and strong durability in 1 M KOH solution.

We report the successful synthesis of cobalt nanoparticle embedded porous nitrogen doped carbon nanofibers (Co-PNCNFs) by a facile and scalable electrospinning technology. The electrospun Co-PNCNF composite exhibits a low onset potential of 1.45 V (vs. RHE) along with high current density (overpotential of 285 mV for  $10 \text{ mA cm}^{-2}$ ) towards OER. The exceptional performance could be ascribed to the bi-functionalized CNFs with nitrogen doping and cobalt encapsulation, which can convert the inert carbon into active sites. Moreover, the porous structure and synergistic effect further provide a highly effective surface area and facilitate a fast electron transfer pathway for the OER process. Interestingly, the Co-PNCNF composite also displays the capability for the hydrogen evolution reaction (HER) in alkaline solution. A water electrolyzer cell fabricated by applying Co-PNCNFs as both anode and cathode electrocatalysts in alkaline solution can achieve a high current density of  $10 \text{ mA cm}^{-2}$  at a voltage of 1.66 V.